

## MARALKYD 5110 PRIMER

PRODUCT DATA SHEET

high-quality, single-component alkyd resin based zinc phosphate primer, that combines excellent corrosion protection with fast drying and easy application. This primer has been specially developed for professional use in construction workshops and industrial environments where reliability and efficiency are paramount. Thanks to its high-build properties, effective protection is achieved with just one coat

**Type:** Alkyd resin-based fast drying primer

**Usage:** Machine Industry, Light Industry, Steel Industry, Manufacturing Industry, Wooden Body Industry.

### Physical Information:

<b>Finish:</b>	Matt
<b>Colors:</b>	Standard colours (e.g. RAL)
<b>Volume Solids:</b>	50 % ± 2 (varies depending on color)
<b>VOC (mixed):</b>	455 g/l
<b>Density:</b>	At 20 °C 1.5 ± 0.1 kg/l (varies depending on color)
<b>Theoretical Coverage:</b>	At a dry film thickness of 50 µm: 10 m <sup>2</sup> /l
<b>Heat Resistance:</b>	120 °C (dry load)
<b>Shelf life:</b>	In original well shut packaging 12 months, stored inside at temperatures between 5 °C and 40 °C.
<b>Potlife:</b>	-
<b>Thinner:</b>	Markaj Industrial Thinner

### Processing Data

	Airless spray	Brush-roller	Airspray
<b>Thinner</b>	-	-	-
<b>Amount</b>	5 vol.%	10 vol.%	10-20 vol.%
<b>Nozzle</b>	min. 0.021 inch	n.a	1.2-1.7 mm
<b>Flow pressure</b>	160 bar	n.a	3-5 bar
<b>Dry film thickness</b>	80 µm	80 µm	80 µm

**Cleaning tools:** Immediately after application using thinner - Markaj industrial thinner.

**Mixing Instructions:** preferably using a mechanical mixing device. The temperature of the mixed product should at least be 10 °C during application.

### Drying Times

	10 °C	20 °C
<b>Touch:</b>	1 hour	20 mins
<b>Handle:</b>	2 hours	1 hour
<b>Recoat:</b>	2.5 hours	40 mins

## MARALKYD 5110 PRIMER

PRODUCT DATA SHEET

### Surface Preparation

**Steel Roughness** profile 10 – 25 µm

**Untreated Steel** The surface needs to be pretreated according ISO12944 part 4 § 6.2.3. Remove grease, oil, dirt etc. upon cleaning by sandblasting, phosphating or mechanical methods.

### Application Conditions

Application temperature should be in the range of 5°C to 40°C to get the perfect result. Keep application area well ventilated during application and drying, in order to reduce evaporated solvents. This is necessary to acquire good drying conditions and for the good of the applicators' health.

### Environment and health

Harmful and irritating in contact with skin, eyes and by inhalation. In case of eye contact, immediately wash with large amounts of water and contact a medical expert. Do not eat, drink or smoke during application.

### Maintenance

It is recommended to clean the surface regularly and to inspect the coats of paint for defects annually. Touch up any defects with the original paint system.

### Packaging

5kg, 20kg and 25 kg cans.

*Notes: All information provided in this technical bulletin may change from time to time as a result of experience, developments in raw materials, and research and development activities. For additional information, please contact your regional sales representative or MARKAJ directly (Istanbul).*